



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 38/00, A23J 1/00, C01B 17/62	A1	(11) International Publication Number: WO 97/33600 (43) International Publication Date: 18 September 1997 (18.09.97)
(21) International Application Number: PCT/US97/03800 (22) International Filing Date: 12 March 1997 (12.03.97) (30) Priority Data: 08/614,373 12 March 1996 (12.03.96) US 08/814,219 11 March 1997 (11.03.97) US (71) Applicants (for all designated States except US): MIDWEST GRAIN PRODUCTS, INC. [US/US]; 1300 Main, Atchison, KS 66002 (US). WATSON FOODS CO., INC. [US/US]; 301 Heffernan Drive, West Haven, CT 06516 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): BASSI, Sukh [US/US]; 1502 Hillcrest Court, Atchison, KS 66002 (US). MANINGAT, Clodualdo, C. [PH/US]; 15995 Country Lane West, Platte City, MO 64079 (US). CHINNASWAMY, Rangaswamy [IN/US]; 4640 N. Holly Court, Kansas City, MO 64116 (US). NIE, Li [CN/US]; 6627 N. Camden Avenue, Kansas City, MO 64151 (US). WEIBEL, Michael, K. [US/US]; 120 Gallows Hill Road, West Redding, CT 06896 (US). WATSON, John, J. [US/US]; 21 Delaware Road, Easton, CT 06612 (US).		(74) Agent: COLLINS, John, M.; Hovey, Williams, Timmons & Collins, Suite 400, 2405 Grand Boulevard, Kansas City, MO 64108 (US). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: MODIFIED WHEAT GLUTENS AND USE THEREOF IN FABRICATION OF FILMS (57) Abstract <p>Gluten protein-based biodegradable or edible films are produced using aqueous, essentially alcohol-free casting dispersions containing modified protein (preferably wheat gluten protein) and a plasticizer. The modified protein is prepared by treating purified naturally occurring wheat protein with a reducing agent (e.g., sodium metabisulfite) in order to reduce the average molecular weight of the wheat protein and to cleave disulfide bonds therein. Such modified wheat gluten protein lowers the viscosity and allows increased solid contents in the casting dispersions, allowing fabrication of improved films using continuous casting techniques and without use of organic solvents.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Larvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

-1-

MODIFIED WHEAT GLUTENS AND USE THEREOF IN FABRICATION OF FILMS

5

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention is broadly concerned with modified glutens and dispersions which can be used in the casting of biodegradable and/or edible gluten-based films. More particularly, the invention pertains to such glutens, gluten products, 10 dispersions and films, and methods of fabricating the same, wherein wheat gluten is modified with a reducing agent for cleaving of disulfide bonds therein under controlled conditions which improve the rheological properties of the grain protein. Such modified wheat glutens can be used to fabricate superior films having good strength and thermal sealing properties. The dispersions of the invention can be continually cast into 15 films using commercial film-forming equipment and without use of organic solvents.

Description of the Prior Art

Grain proteins, such as those derived from soy protein, or wheat or corn gluten, are commercially available and are relatively inexpensive in comparison to other biomaterials and many synthetic polymers. It has been suggested that such grain 20 proteins and particularly the modified wheat glutens can be used to form flexible films by solution or dispersion casting, provided that the wheat glutens are used with appropriate plasticizers. Generally, it is understood that such films are insoluble in water and have good moisture permeability, but are deficient in oxygen permeability and tear strength. 25

In many film-forming prior procedures, the gluten-based casting solutions are prepared with alcohol and are heated to levels which substantially denature the gluten proteins and gelatinize the starch content of the solution. See, e.g., U.S. Patent No. 3,653,925. The use of alcohol solvents renders commercial-scale processing difficult and dangerous owing to explosion hazards. Heat denaturation of the gluten proteins 30 lowers the ultimate strength of the films and the gelatinized starch further weakens the films and creates non-transparent films.

There is accordingly a real and unsatisfied need in the art for improved techniques and products for the fabrication of wheat gluten-based biodegradable and/or

-2-

edible films which yields films having better physical properties while avoiding use of large quantities of alcohol as a part of film casting solutions or dispersions.

SUMMARY OF THE INVENTION

5 The present invention overcomes the problems outlined above, and provides enhanced modified gluten, gluten products and dispersions, and gluten-based films having superior physical properties. Generally speaking, the improved products of the invention are based upon use of highly concentrated, substantially undenatured modified wheat gluten. Broadly, a starting gluten material is treated with a reducing agent in order to lower the average molecular weight of the gluten proteins, and also to
10 cleave in a controlled way a proportion of the disulfide bonds of the proteins. Such a modified wheat gluten product can be prepared and dried for later use. In such cases, the dried product is added to an aqueous liquid phase which is essentially alcohol-free (preferably no more than about 2% by weight alcohol and more preferably completely
15 alcohol-free) including a plasticizer to form a modified gluten film casting dispersion. Alternately a casting dispersion can be made directly from starting gluten by treatment with a reducing agent and addition of a plasticizer.

 In film-forming procedures, the modified wheat gluten dispersions of the invention are layered onto a substrate and dried. Preferably, the film drying is done as
20 a high temperature-short time operation. Final dried films in accordance with the invention have excellent tear strength and thermal sealing properties.

BRIEF DESCRIPTION OF THE DRAWING

 The single drawing is a schematic flow diagram illustrating the preferred
25 processing steps for obtaining modified wheat gluten products and dispersions, and wheat gluten-based films.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

 Turning to the drawing, preferred processes in accordance with the invention are schematically set forth with particular reference to the use of wheat gluten as the starting material to produce modified wheat glutens, modified wheat gluten products and dispersions, and resulting wheat gluten films.
30

 Referring to the drawing, a preferred process of the invention begins with provision of wheat gluten starting material 10. In the illustrated process, conventional
35 wet dough from a wheat gluten production process may be used, having about 75% by

-3-

weight wheat gluten on a dry basis. In order to provide the most suitable starting material for the formation of film-forming dispersions, the gluten dough in step 10 should be concentrated to achieve a gluten protein content of at least about 85% by weight, and more preferably from about 85-95% by weight (dry basis). Advantageously, the concentrated wheat gluten material should have a maximum of about 10% by weight of naturally occurring brans, starches and other insolubles, and more preferably from about 0.1-8% by weight thereof. Generally, in order to obtain such high protein content, low insolubles wheat gluten, it is necessary to remove naturally occurring brans, starches and other insolubles from the commercially available wet dough.

In one aspect of the invention, the gluten starting material 10 is treated to form a modified gluten protein product which is dried and then used to form a casting dispersion. This exemplary process is illustrated in the drawing in steps 12-16, inclusive. In particular, in the first step 12 of this process, the high gluten protein starting material is treated with a reducing agent and centrifuged to form a modified gluten protein product. The function of the reducing agent is to cleave disulfide bonds in the gluten protein, and to lower the average molecular weight thereof. Preferably, the modified gluten protein product has an average molecular weight of up to about 3000 kDa, and more preferably up to about 1000, and most preferably from about 50-900 kDa; moreover, the product should have at least about a 5% reduction in disulfide bonds as compared with the naturally occurring gluten protein in the gluten starting material, and more preferably from about a 25-100% reduction in disulfide bonds.

The reducing agents useful in the context of the invention are preferably taken from the group consisting of the alkali metal and ammonium sulfites, bisulfites, metabisulfites and nitrites, and mercaptoethanol, cysteine, cysteamine, and ascorbic acid; the alkali metal metabisulfites are most preferred. The amount of reducing agent used should be at a level of from about 0.05-20% by weight, based upon the weight of the wheat gluten protein in the wheat gluten starting material taken as 100% by weight. A more preferred range in this respect is from about 0.05-1% by weight on the same basis. In practice, the treatment of step 12 involves contacting the gluten starting material with an aqueous solution of reducing agent at ambient room temperature. The centrifugation step is conventional and is carried out in order to remove insoluble brans, starches and other insolubles and thereby increase the protein content of the starting dough.

Step 14 as illustrated in the drawing involves conventional spray drying the modified gluten protein product in order to yield a powder. Normally, this powder would have a maximum moisture content of about 10% by weight, more preferably up to about 7% by weight. The powder itself has an extended shelf life, and can be sold as a product of commerce to customers wishing to fabricate gluten-based films.

Referring to step 16, the dried modified gluten protein product is added to an aqueous, essentially alcohol-free liquid phase which includes a plasticizer in order to form a modified protein dispersion. Such a dispersion would typically include from about 15-25% by weight gluten protein. In addition, the liquid phase would normally include a member selected from the group consisting of acids and bases for altering the pH of the liquid phase in order to promote the dispersion of the modified gluten protein therein. Optional ingredients can also be used in the liquid phase, for example, a release agent, colorant and defoamer.

In preferred forms, the plasticizer is a polyol, a modified polyol or polymeric alcohol or polyol or urea. The plasticizer is advantageously selected from the group consisting of glycerol, diglycerol, propylene glycol, triethylene glycol, sorbitol, mannitol, maltitol, hydrogenated starch syrup, polyvinyl alcohol, polyethylene glycol, urea and mixtures thereof; glycerol is the most preferred plasticizer. In terms of levels of use, the plasticizer is employed in an amount sufficient to lower the glass transition temperature of the final film below about 25°C. Thus, the plasticizer is preferably present at a level of from about 15-40% w/w, and more preferably from about 25-30% w/w, based upon the weight of modified gluten protein taken as 100% by weight. The water content of the modified gluten protein dispersions would be up to about 85% by weight and more preferably from about 75-80% by weight.

The pH adjusting agent is most preferably a base, with sodium hydroxide, potassium hydroxide and ammonia being most preferred. Generally, sufficient base should be added to adjust the pH of the modified gluten protein dispersions to a level of about 8-12, and most preferably from about 8.5-11.5. Such pH levels are usually achieved by using from about 1-15% w/w base, with the weight of the modified gluten protein taken as 100% by weight, and more preferably from about 1.5-10% by weight on this basis.

Release agents are very commonly used and are selected from the group consisting of the alkali salts of long chain fatty acids (C₈-C₂₂) as well as glycerol sorbitol monostearates; particularly the potassium and sodium salts of palmitic and stearic acids and combinations thereof. Release agents are normally used at a level of

from about 0.05-2% w/w (more preferably from about 0.3-0.8% w/w) based upon the protein content of the dispersion taken as 100% by weight. Release agents facilitate separation of final films from a casting substrate.

5 Defoamers if used are added to aid in the process of degassing of the modified gluten protein dispersion before casting thereof. Many commercially available defoamers can be used in minor amounts for this purpose, typically up to about 5% by weight, based upon the weight of the modified gluten protein taken as 100% by weight. Obviously, if edible films are desired, food grade defoamers would be used.

10 Colorants can be added to the modified gluten protein dispersion in order to give a desired color to the final films. The amount of colorant used is typically less than 1% by weight, based upon the weight of the modified gluten protein taken as 100% by weight.

15 In preparative procedures, it is important that the modified gluten protein dispersions be prepared without excessive heat in order to insure that the modified gluten protein content of the dispersions is not substantially heat denatured. To this end, the dispersions of the invention are preferably made with agitation but at a temperature below about 40°C, and most preferably below about 32°C. In this way, one can be assured that the modified gluten protein content of the dispersion is not rendered insoluble or otherwise unacceptably denatured.

20 As indicated, it is normally desirable to degas the modified gluten protein dispersions prior to casting. This is usually done under vacuum conditions so as to render the dispersions essentially free of entrained air bubbles.

25 The final modified gluten protein dispersions useful for direct film casting would normally have a viscosity of from about 5000-25,000 cps (Brookfield at 10 rpm), and more preferably from about 7000-12,000 cps. Moreover, they would be maintained at relatively low temperatures, and preferably no more than about 40°C, and preferably up to about 32°C. In casting procedures as referred to in step 18, the prepared dispersions are layered by known means onto a substrate such as a stainless steel plate or belt to achieve a substantially uniform thickness (a wet thickness of from about 2-50
30 mils, more preferably from about 6-12 mils). The layers are then dried at a controlled temperature and humidity to give the final films. Preferably, the drying procedure should be carried out at relatively high temperatures and short drying times. For example, the drying temperature (i.e., of the belt environment) is preferably from about 60-99°C (more preferably from about 70-85°C), with a drying time of up to about 10
35 min., and more preferably from about 1-5 min. The humidity conditions in the drying

-6-

chamber should also be controlled, to achieve an initial relative humidity of from about 5-50%, more preferably up to about 10%.

5 The wet gluten dough from step 10 may alternately be treated via steps 20-22 as shown in the drawing to form a modified gluten protein dispersion. In this process, the starting wet dough is initially treated with base and centrifuged followed by spray drying to form the desired concentrated dried wheat gluten having at least about 85% by weight wheat gluten protein content. Thereafter, the dried wheat gluten may be modified by adding it to a liquid phase including reducing agent and plasticizer to directly form the modified wheat gluten protein dispersion (step 22). In this instance, 10 the dried wheat gluten is subjected to the reducing agent in the presence of the plasticizer so that the gluten is treated to reduce the average molecular weight thereof and to cleave disulfide bonds at the time the casting dispersion is formed. This dispersion can then be used to form the wheat gluten film in step 18 as indicated in the drawing.

15 Another alternate procedure depicted in the drawing involves direct formation of a modified gluten protein dispersion from commercially available vital wheat gluten (step 24). In such an alternative technique, the vital wheat gluten starting material is directly added to a liquid phase including at least a reducing agent and a plasticizer to directly form a modified gluten protein dispersion. Also, a filtering step is employed 20 to reduce the content of the bran, starch and other insolubles and thereby elevate the wheat gluten protein content of the dispersion. In this case, the amounts and preparative procedures described previously in connection with the first method of preparation are followed. Similarly, once a modified gluten protein dispersion is formed in step 22, the casting thereof in step 18 is carried out exactly as described.

25 Final gluten films in accordance with the invention have very desirable strength and thermal sealing abilities. Moreover, the films hereof can be readily controlled in terms of color and opacity. As indicated above, the modified gluten protein content of the casting dispersions are subjected to disulfide bond cleavage owing to the treatment with reducing agent. It is to be understood however, that the film drying process serves 30 to reform many of these disulfide bonds to increase the tear strength of the final films. In this connection, the gluten-based films of the invention comprise a matrix of modified gluten protein and a plasticizer. It is believed that the modified gluten protein present in the final films is somewhat different than that present in the casting dispersions. As indicated previously, the plasticizer is present in the final film in an 35 amount to lower the glass transition temperature thereof to below about 25°C. This

-7-

translates to a plasticizer content of the films of from about 15-40% by weight, and more preferably from about 25-30% by weight. The final moisture content of the films of the invention would be up to about 15% by weight, and more preferably from about 5-10% by weight.

5 The other ingredients would include the release agent and colorant. The release agent would normally be present at a level of up to about 2% by weight, based upon the weight of the modified gluten protein content of the films taken as 100% by weight. The colorant will of course be present at a level necessary to give a desired color.

10 Although the films can be of variable thickness, normally they have a thickness of up to about 50 mils and more preferably from about 2.5-20 mils. The films of the invention would generally have tensile strengths of from about 50-300 kg/cm² and more preferably from about 75-250 kg/cm². Tear moduli would range from about 1.0-60, more preferably from about 2-50. Elongation values may vary from about 50-300%, more preferably from about 60-200%.

15 The following examples set forth presently preferred techniques for the preparation of modified wheat gluten protein products, modified gluten protein dispersions, and resultant gluten-based films. It should be understood in this respect that the examples are provided by way of illustration only, and nothing therein should be taken as a limitation upon the overall scope of the invention.

20

Example 1

Seventy-five parts by weight of wheat gluten isolate (Midwest Grain Products, Inc.) was blended with 25 parts by weight food grade glycerol (99%, Sigma Chemical Co.) using a Hobart mixer. The mixed sample was gradually transferred to a homogenizing tank containing 347 parts by weight water, 0.15 parts by weight sodium metabisulfite, 1.5 parts by weight sodium hydroxide, 0.45 parts by weight potassium stearate and 0.9 parts by weight Mazu DF203 defoamer (PPG Industries, Inc.). Creation of the modified gluten protein dispersion took about 10 minutes and the final dispersion temperature was 25°C. Thereafter, the modified gluten protein dispersion was degassed under vacuum to give a viscous dispersion essentially free of air bubbles.

30 The complete modified gluten protein dispersion was then applied onto a stainless steel plate using a film applicator to give a film thickness of about 3 mils. The applied film was then dried for about 3 minutes in a closed oven at a constant temperature of 90°C. The dried film was then readily peeled from the plate.

35

-8-

Example 2

The process of Example 1 was repeated, except vital wheat gluten (approximately 75% by weight wheat gluten protein) is used instead of wheat gluten isolate. Prior to degassing, the modified gluten protein dispersion was pressure filtered to remove bran, starch and other soluble materials.

Example 3

A dried modified high protein wheat gluten product was prepared by purification of wet gluten dough from a commercial gluten production process (Midwest Grain Products, Inc.). Wet gluten dough containing 100 parts by weight gluten solids was dispersed in a 1% ammonia solution to give a solids content of 14% by weight. 0.5 parts by weight sodium metabisulfite was then added to the ammonia-gluten dispersion. After 5 minutes set time, the ammonia-gluten dispersion was centrifuged to remove most of the insolubles. The purified modified gluten protein product was then spray dried to give a dried modified gluten protein product having a protein content of about 90% by weight, dry basis.

The dried modified gluten protein product was then dispersed in a liquid phase for film production. In particular, 75 parts by weight of the dried modified gluten protein product were mixed with 25 parts by weight food grade glycerol in a Hobart mixer. The mixed sample was transferred to a homogenizing tank containing 347 parts by weight water, 1.5 parts by weight sodium hydroxide, 0.6 parts by weight stearic acid and 0.9 parts by weight Mazu DF203 defoamer to create a modified gluten protein dispersion. The dispersion took about 10 minutes to form. The dispersion temperature was maintained throughout at about 25°C. After formation of the modified gluten protein dispersion, it was degassed under vacuum to give a viscous dispersion essentially free of air bubbles. The modified gluten protein dispersion was then applied to a stainless steel plate with a film applicator to give a layer which resulted in a final film thickness of 3 mils. The layer was dried in a closed oven with a control temperature of 90°C over a period of about 3 minutes. The dried film was readily peeled from the plate.

Example 4

The process of Example 1 was repeated except that the modified gluten protein dispersion was formulated using 7.5 parts by weight ammonia in lieu of sodium hydroxide.

-9-

Example 5

In this example, a wheat gluten isolate having a protein content ($N \times 6.25$) of 92.5% by weight and a moisture content of 5.0% by weight was used to prepare a master batch casting solution of the type referred to in step 22 of the Figure. A total of 27 pounds of the wheat gluten isolate were carefully dispersed into 59 pounds of an alkaline (potassium hydroxide, Fisher Scientific Co.) cold water solution (16°C) containing an antifoam agent (BASF L-121) and sodium metabisulfite (Fisher Scientific Co.) reducing agent by slow serial addition of five pound aliquots of the gluten isolate to the alkaline solution. Mixing and dispersion of the gluten isolate was carried out in a 50 gallon liquifier (Breddo Corporation). After initial fluidization of the gluten isolate was achieved, 15 pounds of ice was added to the mixture and high intensity mixing was continued to completely hydrate and disperse all gluten particles and agglomerants as evidenced by the absence of any visible, physical heterogeneity in a draw-down film. The high intensity mixing was completed after 15 minutes at which time the temperature of the mixture was 29°C. An 8 gallon aliquot of the master batch mixture was withdrawn and immediately vacuum degassed for 15 minutes at a vacuum pressure of -28 inches Hg using a stirred 25 gallon reactor.

The final batch mixture totaled 101 pounds, containing 27 pounds of the gluten isolate, 0.5 pounds (1.85% w/w based on the protein content taken as 100%) antifoam agent, 0.65 pounds (2.5% w/w based on the protein content taken as 100%) potassium hydroxide, 56.75 g (0.46% w/w based on the protein content taken as 100%) reducing agent, with the balance being water. The pH of the final mixture was 11.2. Rotational viscometry measurements using a Brookfield RTV viscometer at 10 rpm gave viscosities of 8000, 9600 and 15,200 cps at mixture temperatures of 27°C, 21°C and 17°C respectively.

The theoretical concentration of the master batch mixture was 24.7% by weight protein solids with other non-volatile solids estimated at 0.7% by weight for an approximate total solids content of 25.4% by weight. The experimentally determined non-volatile solids content (16 hours at 105°C) was 25.6% by weight, a good agreement with the theoretical value considering some evaporative losses during vacuum degassing.

It was found that the master batch mixture did not undergo significant changes in physical characteristics over several weeks storage, if it was immediately stored under refrigerated conditions at about 4°C with care taken to maintain substantially anaerobic conditions.

-10-

A series of tests mixtures containing the master batch mixture as well as plasticizer (either glycerine or propylene glycol (PG)) and release agent (5% aqueous solution of potassium stearate) were prepared using 500 g aliquots of the master batch mixture (estimated to contain 128 g of protein) according to the following recipes. In each case, the mixtures were prepared by adding the appropriate amount of plasticizer and release agent to the 500 g aliquot in a 1 liter beaker and carefully mixing the contents on a Cafamaro mixer at low speed using a paddle blade stirrer assembly to avoid incorporation of excess air. All percent w/w values are based upon the protein content of the preparations taken as 100% by weight.

Table 1

Experiment #	Glycerine	Propylene Glycol	Potassium Stearate
1	25.0 g (20% w/w)		12.5 g (0.5% w/w)
2	31.3 g (25% w/w)		12.5 g (0.5% w/w)
3	37.5 g (30% w/w)		12.5 g (0.5% w/w)
4		25.0 g (20% w/w)	12.5 g (0.5% w/w)
5		31.3 g (25% w/w)	12.5 g (0.5% w/w)
6		37.5 g (30% w/w)	12.5 g (0.5% w/w)

The test mixtures described above were formed into films using a continuous casting assembly. The latter consisted of a stainless steel belt casting surface moving over segmented, serial steam chests heating the belt from below and a high velocity, countercurrent heated air tunnel above the belt surface with initial relative humidity of less than 10%. The belt was 24 inches wide whereas the air tunnel drying chamber had a length of 60 feet. Three of five existing steam chests were employed in these tests, giving a belt temperature in the presence of the countercurrent air flow above the belt estimated to be 80-85°C. A simple gravity-fed casting box with a vertically adjustable casting bar was positioned above the belt adjacent to one end thereof to feed the test mixtures (at ambient temperature of about 21°C) onto the moving belt casting surface. Adjustment of the casting bar allowed regulation of the wet film thickness (typically 9-10 mils). The belt speed (and hence the residence time in the drying chamber) was variable and typically was maintained at about 17-20 ft/min. for an average residence time in the chamber of 3-4 min.

All films were cast with a width of 6-8 inches and displayed good belt adhesion in the drying tunnel with excellent release characteristics to the downstream rewind collection spool. All test films were heat sealable with good physical handling characteristics.

The test films were examined for standard physical properties. Tensile strengths were measured on a Single Strand Strength Tester Model 3A (Alfred Suter Co.) and were expressed as applied force/cross-sectional area (kg/cm²). The relative tear moduli were measured with an Elmendorf Tearing Tester (Albert Instrument Co.). These test results are tabulated in Table 2 and are the average of the three test swatches of each film.

Table 2

Test Film #	Thickness (mil)	Tensile Strength (kg/cm ²)	Tear Modulus
1 (20% glycerine)	3.02	180	5.3
2 (25% glycerine)	2.97	117	24.7
3 (30% glycerine)	4.69	78	40.6
4 (20% PG)	3.14	203	2.0
5 (25% PG)	3.46	215	4.7
6 (30% PG)	3.08	133	9.3

These test results confirmed that continuous cast films having good mechanical properties can be prepared from aqueous gluten protein mixtures without use of alcohol or other solvents. Both glycerine and PG are good plasticizers for gluten isolate based-films with tensile strength and tear modulus varying inversely and directly, respectively, for increasing concentration of plasticizer relative to protein content.

Example 6

A master batch casting mixture was prepared in a manner similar to that of Example 5 except that the initial temperature of the alkaline dispersing solution was 10°C. This extended the mixing time window to 30 min. before reaching 28°C. After degassing the viscosity of the mixture was 8000 and 10,000 cps at 27°C and 24°C, respectively. One kg aliquots of the mixture were added to binary plasticizer

-12-

combinations of glycerine and urea (except for a urea-free control) with 0.5% by weight potassium stearate as a release agent for continuous casting tests, using the equipment and methods described in Example 5. The following preparations were used, where all percentage w/w data are based on protein content of the preparations taken as 100% by weight.

Table 3

Experiment #	Glycerine	Urea	Potassium Stearate
1	50 g (20% w/w)		25 g (0.5% w/w)
2	50 g (20% w/w)	6.3 g (5% w/w)	25 g (0.5% w/w)
3	50 g (20% w/w)	12.5 g (10% w/w)	25 g (0.5% w/w)
4	50 g (20% w/w)	18.8 g (15% w/w)	25 g (0.5% w/w)

All test films gave excellent release and physical handling properties. After storage equilibrium at around 20% humidity, films 2-4 became progressively more tacky and film 4 sufficiently fused after 1 month that it could not be unrolled. Film 1 (control) remained pliable and non-tacky after 3 months storage at ambient conditions. The physical properties of the films are summarized in Table 4 (experiment 4 film could not be tested because it was too tacky to unroll).

Table 4

Test Film #	Thickness (mil)	Tensile Strength (kg/cm ²)	% Elongation
1 (20% glycerine/no urea)	2.5	179	70
2 (20% glycerine/5% urea)	2.52	97	110
3 (20% glycerine/10% urea)	2.19	109	177

The tensile strengths of these films are comparable to those of the glycerine series in Example 5. The presence of urea appeared to make the films more elastic as evidenced by the elongation results.

-13-

We claims:

1. A process for the continuous casting of gluten protein-based films comprising the steps of:

5 providing a continuous casting dispersion comprising a modified gluten protein product made from naturally occurring gluten protein and including at least about 85% by weight modified gluten protein, said modified gluten protein being dispersed in an aqueous alkaline liquid phase comprising water and a plasticizer, said protein having an average molecular weight of up to about 3000 kDa,

10 said dispersion being essentially free of alcohol; and

applying a liquid layer of said casting dispersion onto a moving film-forming substrate, and allowing said layer to dry on said substrate to form said film.

15 2. The process of claim 1, said modified gluten protein product comprising modified wheat gluten protein.

20 3. The process of claim 1, said modified gluten protein product having at least about a 5% reduction in disulfide bonds as compared with said naturally occurring gluten protein, said modified gluten protein having substantially no heat denaturation.

4. The process of claim 1, said dispersion having a protein content of from about 15-25% by weight.

25 5. The process of claim 1, said plasticizer being selected from the group consisting of glycerol, diglycerol, propylene glycol, triethylene glycol, sorbitol, mannitol, maltitol, hydrogenated starch syrup, polyvinyl alcohol, polyethylene glycol, urea and mixtures thereof.

30 6. The process of claim 1, said plasticizer being present at a level of from about 15-40% w/w, based upon the content of gluten protein in the dispersion taken as 100% by weight.

35 7. The process of claim 1, said dispersion having a pH of from about 8-12.

-14-

8. The process of claim 1, said dispersion including a release agent.

9. The process of claim 8, said release agent being present at a level of from about 0.05-2% w/w based upon the protein content of the dispersion taken as 100% by weight.

10. The process of claim 1, said dispersion having a Brookfield viscosity of from about 5000-25,000 cps.

11. The process of claim 1, said dispersion having a temperature during said applying step of up to about 40°C.

12. The process of claim 1, said film-forming substrate comprising a continuously moving film-receiving belt.

13. The process of claim 12, said belt being disposed within an elongated drying chamber.


14. The process of claim 1, including the step of allowing said layer to dry at an ambient temperature of from about 60-99°C and an initial relative humidity of from about 5-50%.

15. The process of claim 1, said dispersion being applied as a liquid layer having a wet thickness of from about 2-50 mils.

16. The process of claim 1, said film having a tensile strength of from about 50-300 kg/cm².

17. The process of claim 1, said film having a tear modulus of from about 1.0-60.

18. The process of claim 1, said film having an elongation of from about 50-300%.



INTERNATIONAL SEARCH REPORT

International application No.

PCT/US97/03800

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : A61K 38/00; A23J 1/00; C01B 17/62

US CL : 514/12; 426/656; 423/519

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 514/12; 426/656; 423/519

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

DIALOG, APS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 3,653,925 A (ANKER et al.) 04 April 1972, see entire document.	1-18
Y	US 4,990,349 A (CHAWAN et al.) 05 February 1991, column 5, lines 3-21.	1-18
Y	GONTARD et al. Water and Glycerol as Plasticizers Affect Mechanical and Water Vapor Barrier Properties of an Edible Wheat Gluten Film. Journal of Food Science. 1993, Vol. 58, No. 1, pages 206-211, especially Abstract.	1-18
Y	GENNADIOS et al. Effect of pH on Properties of Wheat Gluten and Soy Protein Isolate Films. Journal of Agricultural and Food Chemistry. 1993, Vol. 41, pages 1835-1839, especially Abstract.	1-18

☒

Further documents are listed in the continuation of Box C.

☐

See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

29 APRIL 1997

Date of mailing of the international search report

02 JUN 1997

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

PHUONG BUI

Telephone No. (703) 308-0196

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/03800

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5,472,511 A (RAYAS et al.) 05 December 1995, see entire document.	1-18
Y	PARK et al. Water Vapor Permeability and Mechanical Properties of Grain Protein-based Films as Affected by Mixtures of Polyethylene Glycol and Glycerin Plasticizers. Transactions of the ASAE. 1994, Vol. 37, No. 4, pages 1281-1285, especially Results and Discussion section.	1-18